

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
6 January 2005 (06.01.2005)

PCT

(10) International Publication Number
WO 2005/000904 A1

(51) International Patent Classification⁷: **C08B 30/12**,
C08L 3/00, 3/02, A61K 31/718, 9/10, A23K 1/16, A23L
1/0522

(21) International Application Number:

PCT/EP2004/006480

(22) International Filing Date: 16 June 2004 (16.06.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
03254097.3 27 June 2003 (27.06.2003) EP

(71) Applicant (for all designated States except US): CER-
ESTAR HOLDING B.V. [NL/NL]; Nijverheidsstraat 1,
P.O. Box 9, NL-4551 LA Sas van Gent (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): SIMON, Jacques,

Georges, Denis, Cenere [FR/FR]; 11, Rue Brissard,
F-92140 Clamart (FR). VANHEMELRIJCK, Jozef,
Guido, Roza [BE/BE]; Landbeekstraat 10, B-1860 Meise
(BE).


(74) Agent: KNOWLES, James, Atherton; Stevens Hewlett
& Perkins, 1 St. Augustine's Place, Bristol BS1 4UD (GB).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,

[Continued on next page]

(54) Title: RESISTANT STARCH COMPOSITIONS



(57) Abstract: Process for sterilising
a resistant starch composition com-
prising: (a) dispersing said resistant
starch composition in oil; (b) heating
the starch/oil dispersion obtained in
step (a) to a target temperature of 100
to 175°C, preferably about 150°C; and
(c) cooling the starch/oil dispersion;
sterilised resistant starch obtained by
this process and uses thereof.

BEST AVAILABLE COPY